

1. Technical specifications

Issued by: Graboplast Floor Covering Manufacturers Ltd.
 H-9023 Győr Fehérvári út 16/b.

Purpose: Technical data of the resilient PVC flooring with backfoam according to MSZ EN 651 sheet vinyl.

2. Application area

For use in area of level very heavy commercial (34).

Transport floorcovering for areas of intensive use.

For information on handling of the product (storing, installation, maintenance) see www.graboplast.hu

3. Technical Data of the Product

Parameter	Dimension	Specification	Tolerance	Test method
Width	cm	140	min.	MSZ EN 426
Thickness	mm	6,0	+0,18; -0,15	MSZ EN 428
Weight	g/m ²	3900	+13%; -10%	MSZ EN 430
Foam layer thickness	mm	4,7	-	MSZ EN 429
Wear layer density	kg/m ³	1250	±50	MSZ EN 436
Dimensional stability (L/C)	%	±0,2	max.	MSZ EN 434
Curling	mm	8	max.	MSZ EN 434
Light fastness	grade	6	min.	MSZ EN ISO 105-B02 3. method
Adhesion resistance of top layer	N/50 mm	50	min.	MSZ EN 431
Abrasion group	-	T	-	MSZ EN 660-1
Wear layer thickness	mm	0,9	0,,81-1,00	MSZ EN 429
Castor chair	visual evaluation	no damage	-	MSZ EN 425
Furniture leg	visual evaluation	no damage	-	MSZ EN 424
Hot weld strength	N/50 mm	240	min.	MSZ EN 684
Residual indentation	mm	0,2	max.	MSZ EN 433

4. Informative Data of the product

Parameter	Dimension	Specification	Tolerance	Test method
Chemical resistance	visual evaluation	high resistance	-	MSZ EN 423
Abrasion resistance (H18 wheel)	mg/1000 circle	250	max.	ISO 9352
Slip resistance	class	DS	-	EN 13893
Foot comfort, indentation after loading of 15 s	mm	0,4	min.	MSZ EN 431
Standard roll length	m	15	-	MSZ EN 426

Valid from:
2009.04.27.

Approved by:
Reményi István Leader of Quality Management