

Grabo commercial vinyl flooring

Technical parameters	Units	Standards	Diamond Standart	Vaporex
DESCRIPTION				
Construction			compact heterogeneous	damp proof underlay
Total thickness	mm	EN 428	2.0	1.4
Wear layer thickness	mm	EN 429	0.7	
Width of roll	m	EN 426	2 / 3 / 4	1.45
Length of rolls	lm	EN 426	20	25/45
Total weight	g/m ²	EN 430	2200	1600
CLASSIFICATION				
Classification	class	EN 685	34/43	
PERFORMANCE				
Abrasion group		MSZ EN 660-1	T	
Residual indentation	max. mm	EN 433	0.1	
Dimensional stability	max.%	EN 434	0.2	0.2
Fire resistance		EN 13501-1	Cfl-s1	Bfl-s1
		DIN 4102/ÖNORM	B1	
		Gost 30402-94	G1	
Slip resistance		DIN 51130	R9	
		EN 13893	DS	
Electrical resistance	kV	EN 1815	< 2	
	Ω	EN 1081	≤ 10 ⁹	
Chemical resistance		EN 423	✓	
Bacterial resistance		EN ISO 846:1999	✓	
Light fastness	grade	EN 20105 B02	6	
Castor chair resistance		EN 425	✓	
Anti-bacterial and fungicid treatment			graboSAN	
Seaming method			heat or cold weld	loose lay installation
Warranty	year		10	7




Graboplast Rt

Graboplast Floor Covering Manufacturers Ltd.
 H-9023 Győr, Fehérvári út 16/b.
 Tel: (+36) 96 506-220
 www.graboplast.hu

Distributed by: